

Shielding Effectiveness of Gold Reference

Shielding Effectiveness Measurement acc. to ASTM D4935-10
 Reference Measurement of Gold Film Specimen
 Sample Size Diameter 160 mm



Report Created on:	2019-09-16 10:34:29
Measurement Date:	2019-02-21 15:52:38
Sample:	Gold Reference
Order:	Sample Report
Technician:	L. Hempe

Marker	Freq	Level
M1	200.0 MHz	33.57 dB
M2	601.0 MHz	31.01 dB
M3	1000.0 MHz	30.29 dB
M4	1499.0 MHz	30.28 dB
M5	1900.0 MHz	29.61 dB

